PHYSICAL TESTING REPORT



Bacs



Dalebrook Supplies Ltd Eastways Industrial Estate Witham Essex CM8 3UA

FAO: Mrs. Jacqueline Thomson

Report of Tests on: Cream Marl Large Melamine Plate 28cm TCM4602 Cream Melamine Marl Plate Your Reference:

Lucideon Reference: (19172)-1597

Date Reported: 21-Jan-2019 **Order Number:**

09-Jan-2019 Date(s) of Test(s): 10-Jan-2019 to 10-Jan-2019 Date Logged:

> **Metal Marking Test** Method PT38

Test Results:

Description of Test Specimen: 1x Plate

Result: There was very slight marking which could be removed with washing.

Final Classification: 1

Three grades of steel were used: a Martensitic steel used in cutlery, and a Ferritic and Austenitic steel used in metal working surfaces in catering establishments. Classification: 0 = No visible marking,1 = Marking but removable by washing in warm water at 45+/-5 deg C with the washing solution and cloth in section 3, 2 = Marking not removable by washing

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.



This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon Limited Queens Road, Penkhull Stoke-on-Trent Staffordshire ST4 7LQ

Page 1 of 2 T +44 (0)1782 764428 enquiries@lucideon.com www.lucideon.com

PHYSICAL TESTING REPORT





Dalebrook Supplies Ltd Eastways Industrial Estate Witham Essex CM8 3UA

FAO: Mrs. Jacqueline Thomson

Report of Tests on: White Ceramic Plate 28cm Your Reference: 0544 White Ceramic Plate

Lucideon Reference: (19172)-1596

Date Reported: 21-Jan-2019 **Order Number: Bacs**

09-Jan-2019 Date(s) of Test(s): 10-Jan-2019 to 10-Jan-2019 Date Logged:

> **Metal Marking Test** Method PT38

Test Results:

Description of Test Specimen: 1x Plate

Result: There was no visible marking with any grade of steel.

Final Classification: 0

Three grades of steel were used: a Martensitic steel used in cutlery, and a Ferritic and Austenitic steel used in metal working surfaces in catering establishments. Classification: 0 = No visible marking,1 = Marking but removable by washing in warm water at 45+/-5 deg C with the washing solution and cloth in section 3, 2 = Marking not removable by washing

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.



Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Page 1 of 2

PHYSICAL TESTING REPORT - METAL MARKING **DALEBROOK MELAMINE**

PHYSICAL TESTING REPORT - METAL MARKING TRADITIONAL CERAMIC

END OF TEST REPORT

Lucideon Reference: (19172)-1597
Customer Reference: TCM4602 Cream Melamine Marl Plate
Description: Cream Marl Large Melamine Plate 28cm





END OF TEST REPORT

Lucideon Reference: (19172)-1596
Customer Reference: 0544 White Ceramic Plate
Description: White Ceramic Plate 28cm

Page 2 of 2 Page 2 of 2