

PHYSICAL TESTING REPORT



Dalebrook Supplies Ltd  
Eastways Industrial Estate  
Witham  
Essex  
CM8 3UA

FAO: Mrs. Jacqueline Thomson

Report of Tests on: Omni White Melamine Mug with Blue Handle 300ml

Your Reference: T3811BL Omni White Melamine Mug

Lucideon Reference: (19172)-1599

Date Reported: 06-Feb-2019

Order Number: Bacs

Date Logged: 09-Jan-2019

Date(s) of Test(s): 01-Feb-2019 to 04-Feb-2019

Determination of Handle Strength of Ceramic Holloware Articles  
Method PT32

No.	Handle Strength Failure Value ft.lbf
1	>0.54
2	>0.54
3	>0.54
4	>0.54
5	>0.54
6	>0.54
7	>0.54
8	>0.54
9	>0.54
10	>0.54
Mean	>0.54

Description of Test Specimen(s): Mug

Sample Compliance: The samples meet the requirements of BS8654: 2015

H - Handle broke; P - Handle detached at point of contact; T - Test piece broke

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

Mrs Sharon Mansfield  
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkhull  
Stoke-on-Trent  
Staffordshire ST4 7LQ  
T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com

PHYSICAL TESTING REPORT



Dalebrook Supplies Ltd  
Eastways Industrial Estate  
Witham  
Essex  
CM8 3UA

FAO: Mrs. Jacqueline Thomson

Report of Tests on: Blue Ceramic Beaker Stacking 260ml

Your Reference: 0403 Blue Ceramic Beaker

Lucideon Reference: (19172)-1598

Date Reported: 06-Feb-2019

Order Number: Bacs

Date Logged: 09-Jan-2019

Date(s) of Test(s): 01-Feb-2019 to 04-Feb-2019

Determination of Handle Strength of Ceramic Holloware Articles  
Method PT32

No.	Handle Strength Failure Value ft.lbf	Nature of Failure
1	0.20	H
2	0.36	H
3	0.27	H
4	0.19	H
5	0.21	H
6	0.24	H
7	0.24	H
8	0.34	H
9	0.23	H
10	0.36	H
Mean	0.26	-

Description of Test Specimen(s): Beaker

Sample Compliance: The samples meet the requirements of BS8654: 2015

H - Handle broke; P - Handle detached at point of contact; T - Test piece broke

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

Mrs Sharon Mansfield  
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkhull  
Stoke-on-Trent  
Staffordshire ST4 7LQ  
T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com

**Lucideon Reference:** (19172)-1599  
**Customer Reference:** T3811BL Omni White Melamine Mug  
**Description:** Omni White Melamine Mug with Blue Handle 300ml



END OF TEST REPORT

**Lucideon Reference:** (19172)-1598  
**Customer Reference:** 0403 Blue Ceramic Beaker  
**Description:** Blue Ceramic Beaker Stacking 260ml



END OF TEST REPORT