

PHYSICAL TESTING REPORT



Dalebrook Supplies Ltd  
Eastways Industrial Estate  
Witham  
Essex  
CM8 3UA

FAO: Mrs. Jacqueline Thomson

Report of Tests on: Omni White Melamine Mug with Blue Handle 300ml

Your Reference: T3811BL Omni White Melamine Mug

Lucideon Reference: (19172)-1599

Date Reported: 21-Jan-2019

Order Number: Bacs

Date Logged: 09-Jan-2019

Date(s) of Test(s): 10-Jan-2019 to 10-Jan-2019

Determination of Thermal Shock Endurance of Holloware Articles

Method PT33

No.	Test Specimen Description	Number of Cycles Completed
1	Mug	10
2	Mug	10
3	Mug	10
4	Mug	10
5	Mug	10
6	Mug	10
7	Mug	10
8	Mug	10
9	Mug	10
10	Mug	10

Boiling Tank Temperature: 98 °C

Cold Bath Temperature: 13 °C

Test specimens are subjected to a maximum of ten cycles.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

Mrs Sharon Mansfield  
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkhull  
Stoke-on-Trent  
Staffordshire ST4 7LQ

T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com

PHYSICAL TESTING REPORT



Dalebrook Supplies Ltd  
Eastways Industrial Estate  
Witham  
Essex  
CM8 3UA

FAO: Mrs. Jacqueline Thomson

Report of Tests on: Blue Ceramic Beaker Stacking 260ml

Your Reference: 0403 Blue Ceramic Beaker

Lucideon Reference: (19172)-1598

Date Reported: 21-Jan-2019

Order Number: Bacs

Date Logged: 09-Jan-2019

Date(s) of Test(s): 10-Jan-2019 to 10-Jan-2019

Determination of Thermal Shock Endurance of Holloware Articles

Method PT33

No.	Test Specimen Description	Number of Cycles Completed
1	Beaker	10
2	Beaker	10
3	Beaker	10
4	Beaker	10
5	Beaker	10
6	Beaker	10
7	Beaker	10
8	Beaker	10
9	Beaker	10
10	Beaker	10

Boiling Tank Temperature: 98 °C

Cold Bath Temperature: 13 °C

Test specimens are subjected to a maximum of ten cycles.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

Mrs Sharon Mansfield  
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkhull  
Stoke-on-Trent  
Staffordshire ST4 7LQ

T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com

**Lucideon Reference:** (19172)-1599  
**Customer Reference:** T3811BL Omni White Melamine Mug  
**Description:** Omni White Melamine Mug with Blue Handle 300ml



END OF TEST REPORT

**Lucideon Reference:** (19172)-1598  
**Customer Reference:** 0403 Blue Ceramic Beaker  
**Description:** Blue Ceramic Beaker Stacking 260ml



END OF TEST REPORT